



TECHNOLOGY MAKES LIFE BETTER

安徽省蚌埠市高新区兴中路 985 号日月科技园

电话: 86-552-3827158

传真: 86-552-3822922

安徽艾约塔硅油有限公司

Iota Corporation Ltd.

Sunmoon industry park, 985 Xingzhong Road, Bengbu, China 233000

Tel: 86-552-3827158

Fax: 86-552-3822922

TDS OF IOTA FINE SIL300A

IOTA FINE SIL300A Extinction powder is special for furniture paint, paint, leather, artificial leather and plastic surface. Its good hardness let the paint film has good wear resistance and scratch resistance. It has strong dispersion & good suspension. There is no hard precipitation by long time leave unused. The refractive index is good.

Main specifications and technical data

Specification	IOTA FINE SIL300A
SiO ₂ (dried)	≥98
Loss on Ignition (9500C) %	4-6
PH Value (5% Suspension)	6.5-7.5
Specific Surface Area g/m ²	≥300
Moisture %	3-5
Partical Size	3μm
Oil Absorption g/100g	≥300
ELSE	Special processed
Packing	10kg/bag

Product features

- Good extinction effect. Could be used to make semi-matte, lambency, full - matte and even matt and other matt painting.
- Good dispersion. It could be dispersed to 15μm by high speed stirring.
- The paint film has good transparency of, does not form fog.
- It has no effect on drying storage and curing of paint.
- The film is flat and smooth, fine and wearable, has good abrasion resistance and impact resistance.

ADD: Sunmoon industry park, 985 Xingzhong Road, Bengbu, China 233000
 Tel: 86-552-3827158; Fax: 86-552-3822922 Website: www.iotasilica.com



TECHNOLOGY MAKES LIFE BETTER

安徽省蚌埠市高新区兴中路 985 号日月科技园

电话: 86-552-3827158

传真: 86-552-3822922

安徽艾约塔硅油有限公司

Iota Corporation Ltd.

Sunmoon industry park, 985 Xingzhong Road, Bengbu, China 233000

Tel: 86-552-3827158

Fax: 86-552-3822922

-
- No influence on the durability and weather resistance of the film.
 - Good anti sinking, do not produce hard precipitation during the storage period.
 - The extinction powders are uniform and feel good.

Products uses

Extinction powder must be fully dispersed in coating, so can play their roles. FINE series products can easily dispersed into the paint by standard high-speed dispersion machine, users must pay attention to blade diameter, container size, the height of the coating slurry, impeller rotational speed and so on are the factors influencing dispersion when doing dispersion.

IOTA CORPORATION LTD.

Add: Sunmoon industry park, 985 Xingzhong Road, Bengbu, China 233000

Tel: 0086-552-3827158 Fax: 0086-552-3822922

Mobile/What's app: 0086-18055290537

WeChat: RachelHo0713

Email: sales04@siliconeoil.net

Website: www.iotasilica.com

ADD: Sunmoon industry park, 985 Xingzhong Road, Bengbu, China 233000
Tel: 86-552-3827158; Fax: 86-552-3822922 Website: www.iotasilica.com